

## PM1303 - Papir afdækningstape

Description	Enkeltklæbende papir crepe tape med solvent baseret naturgummi klæber.
Product properties	Den har en god vedhæftning, er fleksibel, og har en god temperaturlægebestandighed. Kan bruges med de fleste almindelige malingstyper og fortyndere. Kan nemt fjernes uden at tapen knækker, men kan stadigvæk rives over i hånden. Kan bruges i forbindelse med tørring ved hjælp af infrarød lys. Bør ikke udsættes for sollys og bør aftages straks malingen er løbetør.
Applications	Alsided afdækningstape til indendørs anvendelse ved byggeri og reparation, industriafdækning og autolakering. Kan bruges ved ovntørring op til 80°C. (30 min ved 110°C).
Storage and ageing	1 års holdbarhed ved opbevaring i original emballage og ved omkring +20°C - 50% relativ fugtighed - og ikke i direkte sol.
Applying tips	Alle overflader skal være rengjorte og klar til montering. Afrensning foretages bedst med IPA (iso-propylalkohol) og en ren klud. Tapen skal påføres ved hjælp af tryk og over en fast overflade.

### TECHNICAL DATA

Color	Yellow	
Thickness carrier	0.09 mm	3.543 Mils
Thickness total	0.135 mm	5.315 Mils
Adhesion on SS	4.5 N/25mm	1.03 Lbs/inch
Tensile strength length	87 N/25mm	19.87 Lbs/inch
Elongation length	9 %	
Service temperature	Between 0 and 80 °C	Between 32 and 176 °F
Temperature performance (short time)	110 °C	230 °F
Application temperature	minimum 15 °C	minimum 59 °F

Disclaimer: Values shown in this document are averages only. For legal reasons, we emphasize that the information on this data is available "as is" and that Stokvis Tapes, an ITW company, gives no guarantees with respect to the accuracy and completeness nor with respect to interpretations made on the basis of this information. See our applicable delivery conditions. Each user should conduct his own tests to determine the suitability of the product for his intended use and shall assume all risks and liability in connection therewith. Stokvis Tapes cannot be held liable for any damages resulting from the unsuitability of the product. Many factors beyond the control of Stokvis Tapes may affect the use and performance of the product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluates the Stokvis Tapes product to determine whether it is fit for a particular purpose and suitable for the user's method of application. The information is available to the user for viewing, copying and distributing, provided that Stokvis Tapes, an ITW company, is always quoted as the source. The information is intended solely for informational and non-commercial use. Intellectual property: Stokvis Tapes, an ITW company, reserves all rights regarding this document and the information contained herein. Reproduction, use or disclosure to third parties without express permission is strictly forbidden.

Stokvis Tapes Denmark A/S  
 Gydevang 40  
 3450 Allerød

+45 - 48 17 12 11  
 www.stokvistapes.dk  
 info@stokvistapes.dk  
 An Illinois Tool Works Company